

## 50 416 final-/picture varnish, AEROSPRAY

### product name:

- Final-/picture varnish, AEROSPRAY.

### contains:

- Dimethylether, acrylic resin, aldehyde resin, mineral spirit.

### basic information:

- Final varnish for paintings in oil based on high-quality synthetic resins.

### characteristics:

- Glossy
- colourless and elastic
- non-yellowing and age-resistant
- fast drying.

### handling:

- Shake well before use.
- Spray at room temperature by moving the can from one side to the other and from top to bottom and holding the can at a distance of 30 – 40 cm from the vertically positioned or slightly inclined and completely dry object. (Make the change in spray direction away from the picture!)
- May only be applied to the layer of oil paint after it has dried completely, i.e. after 8 – 12 month at the earliest.
- The dried varnish layer remains soluble in *turpentine substitute 50019*, *oil of turpentine 50024 / 50102* or *varnish remover 50060* over a long period.
- The varnish coats normally used in practice give no special UV protection to the paints used! For this reason, we recommend that you use high-quality and lightfast oil paints from the outset as far as possible.
- Any clogged-up spray heads are best cleaned using acetone.
- Store in a cool and dry place.
- Protect from sunlight and do not expose to temperatures exceeding 50°C (122°F).
- Individual pre-tests are required (see footer).

### product labeling:

- Please refer to the individual safety data sheet on our website [www.schmincke.de](http://www.schmincke.de)

DrK/ 01.07.2014

H. Schmincke & Co. GmbH & Co. KG · Otto-Hahn-Str. 2 · D - 40699 Erkrath ·  
Tel.: +49-211-2509-0 · [www.schmincke.de](http://www.schmincke.de) · [info@schmincke.de](mailto:info@schmincke.de)



The described product characteristics and example applications have been tested at the Schmincke laboratory. The information is based on the technical knowledge and experience which are presently available to us. In view of the diversity of applications with regard to painting techniques, materials and working conditions and the numerous possible influencing factors, the information refers to general areas of application. The information provided here does not constitute a legally binding warranty of specific characteristics or of suitability for a specific application; use of the products is thus to be adapted to the user's special conditions and checked by preliminary tests. We are thus unable to guarantee product characteristics or accept any liability for damage arising in connection with the use of our products.